

Technical Information

ARTICLE : PP 0401

PRODUCT : PRO-Paint Industrial Paint Metallic stainless steel

Description

Universal metallic stainless steel paint, fast drying, excellent adhesion and suitable for application on substrates such as metal, concrete, wood, masonry, etc. Very suitable for minor repair and maintenance work. For the best result only apply on a well-prepared substrate.

Applications

Metal Concrete Masonry Wood

Product references

Fast drying Excellent adhesion Very high covering ability High wear resistance

Physical and Chemical Properties

Contents	:	500 ML
Base	:	Acrylic resin
Colour	:	Metallic Beige stainless steel
VOC content	:	Approximately 87 m/m %
Solids content	:	Approximately 13 m/m %
Heat resistant	:	Up to 200°C
Use	:	1 to 2 m ² per layer, depending on object and processing method
Drying time	:	at 23°C and rel. humidity 65%
		Dust-dry after 5 to 10 minutes
		Touch-dry after 10 to 20 minutes
		Hardened/ resprayable after 2 hrs
		(Depending on ambient temperature, humidity and layer thickness)
Storage / Shelf life	:	At least 12 months in tightly closed original packaging on dry, cool and
		frost-free place.
General	:	Do not use below 10°C. Do not apply outside if threatening rain, frost or in
		full sunlight. Never place aerosol can on heat source.

Instructions for use

Before use, carefully read the directions on the packaging and act accordingly.

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and then sand. When using outside remove all moss and algae deposits. Cover the surrounding area. The aerosol can should be at room temperature. Ideal processing temperature 15 to 25°C. Shake the aerosol can well for 2 minutes before use and spray a sample. Distance to the surface to be treated should be approximately 25 to 30 centimetres. Apply in several thin layers. Apply the next layer/layers within 30 minutes or wait until the previous layer has fully hardened. Before applying the next layer shake the aerosol can again. After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).



Technima Benelux B.V.

Hambakenwetering 22A | 5231 DC 's-Hertogenbosch | The Netherlands T +31 73 631 43 45 | E info@technimabenelux.com | I www.technimabenelux.com The effectiveness of our systems is based on material developments of the raw material suppliers and our practical experiences. Nevertheless, we can not be held liable for work performed according to the systems, since the final result is determined by the condition of the substrates and other factors, which are beyond our control. With this issue previously published technical data sheets are invalid.