

# **Technical Information**

# ARTICLE : PP 0630 - PP 0637

**PRODUCT** : **PRO-Paint Marking paint 600ML** 

#### Description

High-quality marker spray for use on stone, concrete, asphalt and metal. A much used product in infrastructure.

Asphalt Dots Fencing

## Applications

Concrete	
Stone	
Metal	
Write	

## **Product references**

Very high covering ability180° valve (can be used upside down)Long lasting adhesionWear resistantTo use in PRO-Paint accessoriesFast dryingResistant against petrol, chemicals and weather influences

#### **Physical and Chemical Properties**

Contents	:	600 ML
Base	-	Acrylic resin
Colour	:	White/yellow/black/green/blue/orange/red/luminous pink
Colours closest to RAL		White (RAL 9003 / RAL9016)
		Yellow (RAL 1018)
		Black (RAL 9004)
		Green (RAL 6032)
		Blue (RAL 5015)
		Orange (RAL 2004)
		Red (RAL 3000)
VOC content	:	Approximately 70 m/m %
Solids content	:	Approximately 30 m/m %
Capacity	:	Approximately 60 metres, depending on substrate and processing method
Drying time	:	Hardened after 16 hrs
		(Depending on ambient temperature, humidity and layer thickness)
Storage / Shelf life	:	At least 12 months in tightly closed original packaging on dry, cool and
		frost-free place.
General	:	Do not use below 10°C. Do not apply outside if threatening rain, frost or in
		full sunlight. Never place aerosol can on heat source.

## Instructions for use

Before use, carefully read the directions on the packaging and act accordingly.

The surface should be clean, dry and free of grease. The aerosol can should be at room temperature. Ideal processing temperature 15 to 25°C. Shake the aerosol can well for 2 minutes before use and spray a sample. Apply the marker spray in the desired width. The aerosol can works in 180° / can be used upside down. After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).



Hambakenwetering 22A | 5231 DC 's-Hertogenbosch | The Netherlands T +31 73 631 43 45 | E benelux@technima.com | I www.technimabenelux.com The effectiveness of our systems is based on material developments of the raw material suppliers and our practical experiences. Nevertheless, we can not be held liable for work performed according to the systems, since the final result is determined by the condition of the substrates and other factors, which are beyond our control. With this issue previously published technical data sheets are invalid.